

# Silverstar Floor and Wall Thin Set Adhesive 307

#### PRODUCT DESCRIPTION

Magikol Silverstar 307 Floor and Wall Thin Set adhesive is a bagged cementitious powder to be mixed with water for installing ceramic tile and natural stone using the thin-set method of installation.

#### **Application**

Can be used for interior applications on floors and walls over masonry, concrete, brick wall, mortar beds and cement plaster

#### **Advantages**

- Dual Purpose for walls and floors
- Easy to use Plastic Consistency
- · Consistent quality, ready to use
- · Proven performance

#### Suitable Substrates

- Cement Mortar Beds
- Ceramic Tile and Stones^
- Cement Plaster
- Brick Masonry
- Cement Terrazzo

Packaging - 20 kg and 30 kg bag

Colour: Grev

# Coverage

Approx 45 - 50 sft per 30 kg bag when trowelled with 1/4" x 1/4" (6mm x 6 mm) square notch trowel

Coverage will vary depending on trowel notch size, type and size of tile and substrate

#### Shelf Life

Factory sealed bags of this product are guaranteed to be of first quality for one (6) months\* if stored off the ground in a dry area. \*High humidity will reduce the shelf life of bagged product.

#### **Cautions**

- •Contains Portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In case of contact, flush thoroughly with water.
- •Do not take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Protect finished work from traffic or damage by other trades for an extended period of time during cold weather conditions. At room temperature conditions 70½F (20½C), protect overnight.
- •Keep out of reach of children.

# TECHNICAL DATA

### **Applicable Standard**

ANSI A 118.1 - 1999; EN 12004 & ISO 13007

#### **Performance Properties**

Magikol Silverstar 307 Floor and Wall thin set adhesive mixed with Water

Complies to EN: C1T

Test	Test Method	Results
Shear Bond		
Porcelain Tile	ANSI A 118.1-	200 psi
28 day cure	1999;F-5.2	(1.3 MPa)
Shear Bond	ANSI A118.1-	170 psi
Porcelain Tile		
Water immersion	1999; C-5.2.3	(1.1 MPa)

Compressive	ANSI A118.4-	2000 psi	
Strength	1999; F-1 (modified)	(13.7 MPa)	

Test		<b>Test Methods</b>	Specification	Result
Physical		Visual	<b>Grey Cementitious</b>	Grey
Appearance			Powder	Cementitious
				Powder
Bulk	Density	Internal		
			1.60 - 1.90 gm/ml	1.78 gm/ml
Flow	Point	Internal	180 – 220 mm	185 mm
Open	Time	IS-15477 -	>20 minutes.	20 minutes
		2004		
Pot	Life	Internal	>30 minutes	220 minutes
Spread		Internal	Spread Easily with	Spread Easily
Ability			Good Notchability	with Good
				Notchability
Adjust		IS 15477 : 2004	05 - 15 minutes	10 minutes
Α	bility			
				0.86 KN
	ensile	IS 15477:2004	> 0.750K N	
Adhesion		Dry Condition		
		After14 day		
	h	IC 15 477.2004	> 0 OOKNI	0.75 (/N
Shear		IS 15477:2004	>8.00KN	8.75 KN
Adhesion		Dry Condition		
		After 14 days		

REMARK ALL APPLCATION TESTS ARE DONE FOR THIN BED FIXING (PROCESS OF TILE FIXING INTO A BED OF AN ADHESIVE NOT EXCEEDING 4 MM IN THICKNESS)

# Working Properties at $70^{0}$ F ( $21^{0}$ C )

Magikol Silverstar 307 Floor and Wall thin set adhesive when mixed with water.

Time to Heavy Traffic	16-24 hours	

Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

#### **INSTALLATION**

#### **Surface Preparation**

All surfaces should be between 40½ F(4½ C) and 90½ F(32½ C) and structurally sound, clean and free of all dirt, oil, grease, loose peeling paint, laitance, concrete sealers or curing compounds. Rough or uneven concrete surfaces should be made smooth. Dry, dusty concrete slabs or masonry should be dampened and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28 days old before application. Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Do not cover expansion joints with adhesive, tile or stone.

#### Mixing

Place clean, potable water & Add Magikol Silverstar 307 powder to the liquid. Use approximately 8L of water for 30 kg of powder.

Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow adhesive to slake for 5-10 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

#### Application:

Apply adhesive to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional adhesive with the notched side. Use the proper sized notched trowel to insure full bedding of the tile. Spread as much adhesive as can be covered with tile. Back butter large tiles to provide full bedding and firm support. Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to imbed tile and adjust level. Check adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile If adhesive is skinned over (not sticky), remove and replace with fresh adhesive.

#### Grouting

Grout installation after a minimum of 24 hours curing time at  $70\ F(21\ C)$ .

**Cold Weather Note:** The setting of Portland cement adhesives are retarded by low temperatures. Protect finished work for an extended period when installing in cold weather. For faster setting, use Magikol Premium 252 or Magikol Premium 290.

Do not set tile when surface temperature is below freezing or when substrate is frozen.

**Hot Weather Note:** The evaporation of moisture in Portland cement adhesives and grouts is accelerated by hot, dry conditions. Apply to dampened surfaces and protect freshly spread adhesive and finished work when installing in temperatures over 95©F (35©C).

#### Cleaning

Clean tools and tile work with water while adhesive is fresh.

## **AVAILABILITY AND COST**

#### **Availability**

For distributor or area dealer information:

Telephone: +91-022-49704245 e-mail: info@magikol.co.in

#### Cost

Contact a Magikol Distributor in your area

#### Magikol Industries LLP.

B 28, Pravasi Industrial Estate, Off Array Road, Goregaon East, Mumbai 400063

Telephone: +91 022 49704245 e-mail: info@magikol.co.in

Website: www.magikol.co.in